

HOW TO DECORATE A THERMAL SHIRT

MATERIALS

- BF DIGITAL PRINTING SUBLISTOP (cod. BF PRINTSU)
- Sporty T-Shirt printed in sublimatic
- Plotter
- Heat Press
- Designed Graphic

APPLICATION INSTRUCTIONS

- Print BF PRINTSU
- Wait at least 8 hours after printing, before proceeding cut.
- Cut BF PRINTSU with a laser 45° blade.
- Weed the BF PRINTREF and remove the excess materials.
- Place the BF MYLAR film on the graphic and remove the air bubbles.
- Take off the graphic from the polyester backing.
- Pre-heat your press to 140 ° C.
- Place the garment on the lower platen of your heat press.
- Place the BF PRINTSU design on the garment.
- Press at 140 ° C for 10 seconds.
- Peel the BF MYLAR.

BF PRINT SUBLISTOP PLUS

BF SUBLISTOP serie was created to be applied on garments printed with dye sublimation. It comes with a built-in barrier to prevent the migration of pigments, keeping the material's original color unaltered even after multiple wash cycles.

It's printable with all solvent, eco-solvent and latex based inks.



**TAKE A PICTURE OF YOUR
CREATION AND POST IT ON
INSTAGRAM WITH @BFLEXITALIA
TAG!**

FOLLOW US ON:



@bflexitalia



@bflexitalia



@B-Flex Italia

www.b-flexitalia.com

SAFETY NOTICE

Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications.

This spec sheet is valid for the following products:

BF PRINTSU. Rev_2019/09