BF PRINTOO-BF PRINTO1

PRINT&CUT



PRODUCT DESCRIPTION

APPLICATION STEPS

Print - do not mirror Cut - 45° blade

Weed excess material

Remove BF MYLAR - hot

Remove from liner

Apply BF MYLAR - remove air bubbles

Place your graphic on the garment

Press it - 140°C/285°F for 10 seconds

Turn on your heat press - heat to 140°C/285°F

BF PRINT00 (semi-matt) and BF PRINT01 (matt) are two polyurethane white films printable with solvent, eco-solvent and latex inks and are suitable for heat transfer on cotton fabrics, polyester and acrylic garments.

Very small letters and logos can be easily cut by all current cutting plotters after the printing process thanks to the self-adhesive PET film carrier.

We recommend using BF MYLAR as a transfer tape.

TECHNICAL DATA



Film: PU/Polyurethane



Thickness: 90µ (±5%)



Liner: adhesive PET



Finish: BF PRINT00 semi-matt BF PRINT01 matt



Inks: solvent, eco-solvent, latex

PLOTTER SETTING

Cut settings: do not mirror



Blade: 45°

Minimum cut: 0,5 cm





APPLICATION

Temperature: 140°C - 285°F



Time: 10"



Liner removal: hot



Pressure: medium - 3,5 bar - 50 PSI



Textile: organic, polyester, mixed

SIZES

H 50 cm	L	25 mt / 12,5 mt / 5 mt
H 75 cm	L	25 mt (upon request)
H 100 cm	L	25 mt (upon request)
H 150 cm	L	25 mt (upon request)

Oeko-Tex Standard 100 Class I



Comply with regulation REACH n°1907/2006/EU

WASH RESISTANCE

First wash after application	wait 12 hours
Max wash temperature*	90°C / 195°F
Dry clean	×
Dryer	×

 $^{^{}ullet}$ Temperatures related on heat transfer vinyl; for the inks features, refer to the data sheet inks producer's.

SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information above mentioned in this page. Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications. Rev_2021/03















